WEICON

Assembly Pastes

Anti-Seize High-Tech Assembly Paste





Metal-free | NSF registration

The assembly paste WEICON Anti Seize High-Tech is high-temperature-resistant, has excellent separating characteristics, is metal-free, neutral to materials and has an NSF registration.

It is particularly suitable when metal-containing pastes can cause electrolytic reactions, when nickel-containing products should or may not be used due to health reasons and when dark metal-containing products should or may not be used for visual reasons.

Technical Data

	Medicinal white oil
	white
(+20°C) DIN 51757	1,42 g/cm ³
	yes
DIN 51350	3.600 N
DIN 51350	3.800 N
DIN 51350 (1min/1000N)	0,7 mm
DIN ISO 2137	310 - 340 1/10 mm
DIN 51807	1 - 90
DIN EN ISO 22007-4	1,574 J/(g·K)
	0,675 W/m·K
DIN EN 60243-1 (20°C)	6,3 kV/mm
DIN EN ISO 9227	> 170 h
DIN EN 62631-3-1	1,0 x 10 ¹⁵ Ω·cm
DIN 51400	<0,1 %
	230 MPa
	0,302 mm ² /s
	-40 °C to +1,400 °C
	DIN 51350 DIN 51350 DIN 51350 (1min/1000N) DIN ISO 2137 DIN 51807 DIN EN ISO 22007-4 DIN EN 60243-1 (20°C) DIN EN ISO 9227 DIN EN 62631-3-1

Friction values

Friction values steel-blank (M10 10.9)	
Total friction coefficient	0,11 (min. 0,10)
Friction coefficients threads	0,12 (min. 0,10)
Friction coefficient head	0,10 (min. 0,09)
Friction value V4A (M10 A4 70)	
Total friction coefficient	0,15 (min. 0,14)
Friction coefficients threads	0,15 (min. 0,13)
Friction coefficient head	0,15 (min. 0,14)
Friction value steel electro-galvanized (M10 10.9)	
Total friction coefficient	0,08 (min. 0,07)
Friction coefficient threads	0,09 (min. 0,08)
Friction coefficient head	0,07 (min. 0,06)

Approvals / Guidelines

ISSA Code	33.402.01/02/03/04/03/
	86/87/88/89
IMPA Code	450882/83/84/85/86/87

Surface pre-treatment

First clean the surface to be lubricated with WEICON Cleaner S, depending on the degree of soiling. If screws have already been used, process with the wire brush and clean with WEICON Cleaner S.

Processing

Clean and degrease surfaces with WEICON Cleaner Spray S. Apply a good quantity of assembly paste with a brush, cloth or sponge. On threads it is important that assembly paste is applied down to the thread root and up to the bottom of the screw head to ensure a good sealing effect. Assembly paste must not be mixed with greases or oils to avoid changes in the material characteristics. Assembly paste does not replace oil or grease lubrication.

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the requested properties are recommended. A claim cannot be derived from them.

EQ 400 01/00/00/04/0E/

W E I C O N

Assembly Pastes

Anti-Seize High-Tech Assembly Paste

Storage

Store in tightly closed original container. Do not store with oxidising agents. Store at room temperature in a dry place. Original sealed containers have a shelf life of 24 months.

Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Available sizes

kg.
. 9
kg.
kg,
) g,
) g,
ml
nite kg,
nite 5 g,
) g,
ōg,

Conversion table

(°C x 1.8) + 32 = °F	Nm x 8.851 = lb·in
mm/25.4 = inch	$Nm \times 0.738 = Ib \cdot ft$
μ m/25.4 = mil	Nm x 141.62 = oz∙in
$N \times 0.225 = Ib$	mPa⋅s = cP
$N/mm^2 x 145 = psi$	$N/cm \times 0.571 = lb/in$
MPa x 145 = psi	$kV/mm \times 25.4 = V/mil$



Note
The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Czech Republic s.r.o. phone +42 (0) 417 533 013 info@weicon.cz

Spain phone +34 (0) 914 7997 34 info@weicon.es

WEICON GmbH & Co. KG phone +49 (0) 251 9322 0 info@weicon.de

Italy phone +39 (0) 010 2924 871

WEICON Romania SRL phone +40 (0) 3 65 730 763

WEICON SA (Pty) Ltd South Africa phone +27 (0) 21 709 0088 info@weicon.co.za WEICON South East Asia Pte Ltd Singapore Phone (+65) 6710 7671 info@weicon.com.sg

WEICON Kimya Sanayi Tic. Ltd. Şti. Turkey phone +90 (0) 212 465 33 65